











Paddington 4x16 | V1

Portobello
America

WALL TILE - GLOSSY

| PHYSICAL PROPERTIES | TEST ASTM | NORTH AMERICAN STANDARD A137.1* | RESULTS FOR GLOSSY FINISH |
|---|---------------|--------------------------------------|---------------------------|
|  Water absorption * | C373 | $\leq 0.5\%$ | $\geq 10\%$ |
|  DCOF Average dynamic coefficient of friction | BOT 3000 test | ≥ 0.42 | N/A |
|  Resistance to freeze/thaw cycling * | C1026 | As reported | N/A |
|  Warpage (edge) | C485 | Warpage $\pm 0.4\%$ or ± 0.05 in | COMPLY WITH ANSI A137.1 |
|  Warpage (diagonal) | C485 | Warpage $\pm 0.4\%$ or ± 0.07 in | COMPLY WITH ANSI A137.1 |
|  Wedging | C502 | $\pm 0.25\%$ or ± 0.03 in | COMPLY WITH ANSI A137.1 |
|  Chemical resistance | C650 | As reported | RESISTANT |
|  Breaking strength | C648 | 125 lbf or greater | COMPLY WITH ANSI A137.1 |
|  Thickness | C499 | Range: 0.04 in | COMPLY WITH ANSI A137.1 |
|  Mohs Hardness | C1895 | Range: 0.04 in | 5 |

* Average values referred to our production and related to the glossy finish of the product.

** Shade Variation may vary by individual product. Please refer to catalog for specifics.

- Be sure to use tiles belonging to the same caliber.
- Test results are available on request.
- Tiles can be slippery when wet. We recommend to make sure that the surface is always dry.
- The information provided can be subject to change.

Sizes /Thickness:

| Thickness [mm] | |
|----------------|--------------|
| | 7.44mm |
| Nominal | 4x16 |
| Actual | 3.937x15.748 |

